

QUILL 250

Comfort, Protection and Durability that you always deserved



Wear Your Attitude

TECHNICAL CHARACTERISTICS

Composition	65% FR Viscose, 33% Aramid, 02% Antistatic
Weave	Twill
Weight	240 GSM (±5%)

Parameters	Test Procedure	Warp	Weft
Tensile Strength	EN ISO 13934-1	650 N	500 N
Tear Strength	EN ISO 13937-2	20 N	20 N
Dimensional Stability	EN ISO 6330 – 60°C; Tumble Dry / EN ISO 5077	±3%	±3%
Heat Shrinkage	ISO 17493:2000	<5%	
Color Fastness	ISO 105 C06	Grade - 4	

CARE INSTRUCTIONS



Standards	Parameters	Result
 EN ISO 11612	Flame spread: ISO 15025 (Surface Ignition)	A1
	Flame spread: ISO 15025 (Edge Ignition)	A2
	Convective Heat: ISO 9151	B1
	Radiant Heat: ISO 6942	C1
	Contact Heat: ISO 12127	F1
 EN 1149-5	Electrostatic Dissipative Behavior	MET
 EN 61482-1-2	Electric Arc Exposure	APC- 1
 NFPA 70E	Electric Arc Exposure: ASTM F1959	HRC2